

This listing of claims will replace all prior versions, and listings, of claims in the application:

LISTING OF CLAIMS:

Claims 1-9 (canceled)

- 10. (Previously Presented)** A non-dusting homogeneous pigment composition, which comprises:
- $\geq 40\%$ by weight of one or more effect pigments,
 - 0.5 - 59.5% by weight of a styrene-modified polyacrylate having an acid number > 90 mg KOH/g,
 - 0.5 - 50% by weight of water and/or an organic solvent or solvent mixture,
 - 0 - 10% by weight of a neutralizing agent, and
 - 0 - 10% by weight of a modifying agent.
- 11. (Previously presented)** A non-dusting homogeneous pigment composition according to Claim 10, wherein the effect pigment is a pearl luster pigment and/or an SiO_2 flake coated with one or more metal oxides.
- 12. (Previously presented)** A non-dusting homogeneous pigment composition according to Claim 11, wherein the effect pigment is a pearl luster pigment of TiO_2 and/or Fe_2O_3 coated on mica.

13. **(Previously presented)** A non-dusting homogeneous pigment composition according to Claim 11, wherein the effect pigment is a pigment of SiO₂ flake coated with TiO₂ and/or Fe₂O₃.
14. **(Previously presented)** A non-dusting homogeneous pigment composition according to claim 10, wherein the styrene-modified polyacrylate is an α -methylstyrene-modified polyacrylate.
15. **(Previously presented)** A non-dusting homogeneous pigment composition according to claim 11, wherein the styrene-modified polyacrylate is an α -methylstyrene-modified polyacrylate.
16. **(Previously presented)** A non-dusting homogeneous pigment composition according to claim 12, wherein the styrene-modified polyacrylate is an α -methylstyrene-modified polyacrylate.
17. **(Previously presented)** A non-dusting homogeneous pigment composition according to claim 13, wherein the styrene-modified polyacrylate is an α -methylstyrene-modified polyacrylate.
18. **(Previously presented)** A non-dusting homogeneous pigment composition according to claim 10, which further comprises at least one: defoamer, surface-active

substance, wetting agent, anti-settling agent, levelling agent, siccative or thixotropic agent.

19. **(Previously presented)** A dry material produced from the non-dusting homogeneous pigment composition of claim 10 by tableting, briquetting, pelletizing, fluidized-bed granulating, granulating, spray-granulating or extruding the pigment composition, optionally in the presence of a solvent, and, optionally, freeing the dry material from the solvent.
20. **(Previously presented)** A dry material produced from the non-dusting homogeneous pigment composition of claim 11 by tableting, briquetting, pelletizing, fluidized-bed granulating, granulating, spray-granulating or extruding the pigment composition, optionally in the presence of a solvent, and, optionally, freeing the dry material from the solvent.
21. **(Previously presented)** A dry material produced from the non-dusting homogeneous pigment composition of claim 12 by tableting, briquetting, pelletizing, fluidized-bed granulating, granulating, spray-granulating or extruding the pigment composition, optionally in the presence of a solvent, and, optionally, freeing the dry material from the solvent.
22. **(Previously presented)** A dry material produced from the non-dusting homogeneous pigment composition of claim 13 by tableting, briquetting, pelletizing, fluidized-bed granulating, granulating, spray-granulating or extruding the pigment

composition, optionally in the presence of a solvent, and, optionally, freeing the dry material from the solvent.

23. **(Previously presented)** A dry material produced from the non-dusting homogeneous pigment composition of claim 14 by tableting, briquetting, pelletizing, fluidized-bed granulating, granulating, spray-granulating or extruding the pigment composition, optionally in the presence of a solvent, and, optionally, freeing the dry material from the solvent.
24. **(Previously presented)** A paint, varnish, printing ink, plastic, automotive finish or powder coating composition, comprising a dry material according to claim 19.
25. **(New)** A non-dusting homogeneous pigment composition according to Claim 10, wherein at least one effect pigment is a pigment based on a platelet-shaped and transparent or semi-transparent substrate or a metal effect pigment.
26. **(New)** A non-dusting homogeneous pigment composition according to Claim 10, wherein the composition comprises $\geq 50\%$ by weight of one or more effect pigments.
27. **(New)** A non-dusting homogeneous pigment composition according to Claim 10, wherein at least one effect pigment is a pigment based on mica or SiO₂ flakes.

28. (New) A non-dusting homogeneous pigment composition according to Claim 10, wherein the composition comprises 5 to 40% by weight of the styrene-modified polyacrylate having an acid number > 90 mg KOH/g.
29. (New) A non-dusting homogeneous pigment composition according to Claim 10, wherein the styrene-modified polyacrylate has an acid number > 100 mg KOH/g.
30. (New) A non-dusting homogeneous pigment composition according to Claim 10, wherein the styrene-modified polyacrylate has an average molecular weight of 500 to 200,000.